

# akurit MH grey

Universal bonding bridge

## mineral bonding bridge

standard plastering mortar GP CS IV acc. EN 998-1

- universal and safe
- not suitable for reinforcing layers



## Applications

- bonding bridge on concrete and XPS-R insulation panel
- adhesive mortar for exterior and interior insulation materials (not ETICS)
- for bonding and fixing thermal insulation panels, wood-wood and multi-layer lightweight panels, cement-bound or mineral-bound panels
- felt-float finish plaster for wall base surfaces
- not suitable for reinforcement or smoothing plaster layers
- for external and interior use

## Properties

- tempered for better bonding
- feltable
- suitable for machine application
- mineral
- behaviour in fire A1 - non-flammable

## Composition

- Grey cement in accordance with DIN EN 197-1
- calcium hydroxide in accordance with DIN EN 459-1
- finely fractionated, crushed limestone sand
- additives for improving bonding to the subsurface
- additives for regulating and improving workability and product properties

## Substrate

### Suitable substrates

- Smooth or slightly absorbent subsurfaces
- normal concrete
- Masonry
- XPS, EPS and mineral wool insulation panels
- Not suitable for subsurfaces containing gypsum

### Condition / Testing

- The subsurface must be even, dry, clean, load-bearing, absorbent and free of adhesion impairing residues, efflorescence and sinter skins.
- For assessing the plaster primer, VOB/C DIN 18350, Section 3, DIN EN 13914-1/13914-2 as well as the plaster standard DIN 18550-1/18550-2 should be observed.
- The load-bearing capacity, particularly of old plaster and old paintwork, must be properly tested (e.g. by carrying out a pull-out test or cross-cut test).
- There must be no visible water film, water droplets or condensation (condensed moisture) on the surface of the substrate.

### Pretreatment

- Non-load-bearing coatings must be completely removed.
- Expanded foam boards with smooth foam skin must be roughened.

# akurit MH grey

Universal bonding bridge

## Processing

### Temperature

- Do not process or allow to dry out at air, material or substrate temperatures below +5°C, or if there is a risk of exposure to night frost, or at temperatures above +30°C, or in direct sunlight, or on heated up surfaces, and/or in windy conditions.

### Mixing / Preparing / Processing

- Suitable for processing by hand, or with conventional plastering machines.
- When mixing manually, first place the quantity of water specified in the technical data in a clean container and then sprinkle in dry mortar. Use clean tap water.
- use a suitable agitator to mix the material until smooth and free of lumps. Leave to rest for a moment and then mix again, adding more water, if required, to achieve the right consistency for applying.
- Do not mix with other products and/or other substances.
- When machine-processing: Adjust the amount of water accordingly to obtain a workable consistency.

### Applying / Processing / Assembling

- Plaster bonding bridge: Apply the material with a broad toothed trowel, e.g. 8 x 8 mm. The mortar in the grooves must be at least 2 mm thick. The subsequent plaster layer can be applied as soon as the bonding bridge has hardened sufficiently. Take care to avoid the formation of a "sinter skin" and to roughen the bonding bridge surface (with a coarse broom, for example) after it has started to harden. Alternatively, you can work "wet in wet".
- Bonding insulation panels: Apply the adhesive over the entire surface using the combed bed method or with a line of adhesive around the panel edges and daubs across the surface. (Adhesive coverage: at least 40%). Further work on the bonded insulation panels can be carried out after sufficient standing time has elapsed and the mortar has hardened. After 2 days to 3 days at the earliest.
- Thin-layer felt-float finish plaster: Apply the material over the entire area with a layer thickness of approximately 3 mm and then felt finish the surface after it has hardened sufficiently.
- Thin-layer bond plaster: Apply the material with a plaster thickness of 3 to 5 mm, strike off evenly and then felt finish after it has hardened sufficiently.
- Do not exceed application thickness of 5 mm.

### Processing time

- Approx. 60 minutes at 20°C and 65% relative air humidity
- Mortar that has already started to harden must never be thinned down with additional water, remixed or applied.

### Drying / Hardening

- Protect from drying out too quickly as a result of sun, wind or draughts.

### Subsequent coating / workability

- Suitable for subsequent coating with lime, lime-cement and cement plasters.
- A coat of silicate, silicone resin or emulsion paint is possible as a base and final coat.

### Tool cleaning

- Clean all tools and equipment with water immediately after use.

### Notes

- Carefully cover adjacent surfaces and components (e.g. windows, window sills, etc.). Wash off contamination immediately with water.
- In interior rooms, start up the heating system slowly to increase the room temperature gradually.

## Packaging

- 25 kg/sack
- loose in silo

## Storage

- Store sacks appropriately and in dry conditions on pallets.
- If stored in its original packaging, the product will keep for at least 12 months from the date of manufacture.

## Quantity required / Yield

- consumption:
  - approx. 5 kg/m<sup>2</sup> for adhering
  - approx. 6.3 kg/m<sup>2</sup> per 5 mm plaster thickness as bonding bridge
- yield: app. 20 l fresh mortar per 25-kg-Bag
- yield: app. 800 l fresh mortar per t

# akurit MH grey

Universal bonding bridge

## Technical Data

<b>Product type</b>	standard plastering mortar GP
<b>Category</b>	CS IV
<b>Set mortar bulk density</b>	approx. 1.5 kg/dm <sup>3</sup>
<b>Compressive strength</b>	≥ 6.0 N/mm <sup>2</sup>
<b>Adhesive tensile strength</b>	≥ 0.5 N/mm <sup>2</sup>
<b>Capillary water absorption</b>	W <sub>c0</sub> according to EN 998-1
<b>Water vapour permeability μ</b>	15/35 (table value EN 1745)
<b>Thermal conductivity λ<sub>10,dry,mat.</sub> for P=50%</b>	≤ 0.61 W/(mK) (table value EN 1745)

All data are average values that were determined under laboratory conditions according to relevant test standards and application tests. Deviations are possible under practical conditions.

## Safety and disposal instructions

### Safety

- This product produces an alkaline reaction when it comes into contact with moisture/water. Therefore ensure that skin and eyes are protected. If it should come into contact with the skin or eyes, rinse them thoroughly with water. See a doctor immediately if it comes into contact with the eyes.
- Follow further instructions in the safety data sheet.

### GISCODE

- ZP1 (products containing cement, low-chromate)

### Disposal

- Dispose of the material in accordance with the official regulations.
- Dispose of hardened product in accordance with the local regulations. Do not allow to enter the sewer system. Dispose of the hardened product in the same way as concrete waste and slurries. Waste code according to the Ordinance on the European Waste Catalogue depending on the origin: 17 01 01 (concrete) or 10 13 14 (concreteste and concrete slurries).
- Completely empty and recycle the packaging.

## General notes

This information sheet provides only general recommendations. Should you have any queries relating to a specific application, please contact our technical sales advisor or call our hotline: +49 541 601-601. Since natural raw materials are used, the values and properties described may vary somewhat. All of the details given are based on our current knowledge and experience and on the assumption that the materials are professionally applied and used for their normal purpose. All of the details are non-binding and do not release users from their duty to undertake their own tests to ensure suitability for the intended application. Due to the effects of different weather, processing and construction site conditions, no guarantee can be given for the general validity of all details. We reserve the right to make changes as a result of further development of the product and applications engineering. The general rules for construction engineering, the valid standards and guidelines, and the technical working guidelines must be observed. The publication of this technical data sheet renders all previous editions of this data sheet void. Please obtain the latest information from our website.