

PFM2

Paving grout

2-component, synthetic resin-bonded, water-permeable paving stone grout mortar

- can also be used in drizzle, then no covering is necessary
- sweeper suction machines suitable
- frost and de-icing salt-resistant
- no water addition necessary
- water-permeable
- for light to medium traffic load



APPLICATIONS

- for repointing and repairing natural, concrete and clinker pavements

PROPERTIES

- self-compacting
- can also be used in drizzle
- Chlorine-resistant after hardening
- sweeper suction machines suitable

COLOURS

- sand, stone grey, basalt

COMPOSITION

- Epoxy resin, Epoxy hardener
- functional fillers

SUBSTRATE

Properties/tests	<ul style="list-style-type: none">■ The required joint depth is at least 30 mm, with bound bedding layer at least 20 mm.■ For surfaces subject to traffic, the joint depth is at least 2/3 of the stone height.■ Dimensions differing from these details are to be agreed with our application technology department.
Pretreatment	<ul style="list-style-type: none">■ The required joint depth should be created by blowing or scoring out the joint. The paving surface should then be cleaned dry.■ Depending on the absorption behaviour the paving surface should be wetted thoroughly several times. However, there should be no standing water in the joints when applying the paving stone grout mortar.■ If necessary, apply tubag FHI over the entire surface of the pavement 24 hours before the jointing work to minimise binder residues (for application see TM tubag FHI).

PROCESSING

Temperature	<ul style="list-style-type: none"> Do not use or allow to dry and harden in air, material or substrate temperatures of less than +5 °C, in the case of expected night time frost or at temperatures of over +25 °C, in direct sunlight, extremely heated substrates and/or in strong wind.
Mixing / Preparation / Processing	<ul style="list-style-type: none"> Add the hardener component to the bucket. Mix the mortar in a compulsory mixer or with a mortar whisk. The mixing time of both components must be at least 3 minutes until optimum mortar consistency (foaming) is achieved. Repotting is recommended. No addition of water is required. Depending on site requirements, up to one litre of water can be added to the mortar during the mixing process to increase the flowability.
Processing	<ul style="list-style-type: none"> After approx. 10 to 15 minutes, the joints are swept lengthways and crossways with a hard broom. After 10 to 15 minutes, the film of binder remaining on the stones is sprayed off with a mist of water.
Processing / Working time	<ul style="list-style-type: none"> Approx. 20 minutes at 20°C and 65% relative air humidity
Drying / Hardening	<ul style="list-style-type: none"> The paving area can be walked on by pedestrians after approx. 24 hours and can withstand full loads at the earliest after 7 days (at +20°C and 60 % rel. humidity). When working indoors, ensure good ventilation.
Cleaning the tools	<ul style="list-style-type: none"> Clean all tools and equipment with water immediately after use.
Notes	<ul style="list-style-type: none"> Working in several steps, intermesh the bedding layer and joint filling by at least 1 m so that the joint filling does not end directly above the end of the last bedding section. Leaking joints should be avoided.

PACKAGING

- 25 kg/PP bucket
- Delivery forms vary from region to region and are not available in all locations.

STORAGE

- Store in the original, unopened packaging in dry, frost-free conditions.
- We recommend that the product be used within 12 months of the date of manufacture.
- For date of manufacture, see separate sticker.

QUANTITIES REQUIRED / YIELD

	Top surface	Quantities required* 8 mm joint width	Quantities required* 12 mm joint width
Large paving units	140 x 160 mm	approx. 4.6 kg/m ²	approx. 6.7 kg/m ²
Small paving units	90 x 110 mm	approx. 6.8 kg/m ²	approx. 9.8 kg/m ²
Mosaic paving	40 x 60 mm	approx. 12.8 kg/m ²	approx. 18.0 kg/m ²

*Calculation example for 30 mm joint depth

PFM2

Paving grout

TECHNICAL DATA

Grain	0,2 – 1,2 mm
Fresh raw density	approx. 1.45 kg/dm ³
Compressive strength	≥ 25 N/mm ²
Joint width	≥ 5 mm
Joint depth	≥ 30 mm, with bonded bedding layer ≥ 20 mm
Processing temperature	+5°C to + 25°C
Processing time	approx. 20 minutes

All data are average values which have been obtained under laboratory conditions in accordance with relevant test standards and application trials at +20°C and 60% relative air humidity. Deviations are possible under practical conditions.

SAFETY AND DISPOSAL INSTRUCTIONS

Safety	■ Follow further instructions in the safety data sheet.
Disposal	■ Leftover, hardened material can be disposed of in accordance with waste code number 08 04 09 (adhesive waste and sealing compound waste containing organic solvents or other dangerous substances).

GENERAL INFORMATION

This information sheet provides only general recommendations. Should you have any queries relating to a specific application, please contact our technical sales advisor or call our hotline: +49 541 601-601. All of the details given are based on our current knowledge and experience and on the assumption that the materials are professionally applied and used for their normal purpose. All of the details are non-binding and do not release users from their duty to undertake their own tests to ensure suitability for the intended application. Due to the effects of different weather, processing and construction site conditions, no guarantee can be given for the general validity of all details. We reserve the right to make changes as a result of further development of the product and applications engineering. The general rules for construction engineering, the valid standards and guidelines, and the technical working guidelines must be observed. The publication of this technical data sheet renders all previous editions of this data sheet void. Please obtain the latest information from our website.