

FL-P

Historical lime plaster

Cement-free base and restoration plaster

standard plastering mortar GP CS I acc. EN 998-1

- recipe with original tubag trass

no picture

APPLICATIONS

- ideal for restoration of historic monuments
- for interior and external use

PROPERTIES

- mineral
- optimised hardening and reduced risk of efflorescence by using original tubag trass
- vapour-permeable
- moisture regulating
- good workability

COMPOSITION

- formulated lime according to DIN EN 459
- graded stone aggregates in accordance with DIN 13139
- mineral lightweight aggregates according to DIN EN 13055

SUBSTRATE

Suitable substrates	<ul style="list-style-type: none">■ All types of masonry■ primarily historic masonry■ Concrete■ Plaster base anchored in the plaster primer
Properties/tests	<ul style="list-style-type: none">■ The subsurface must be even, dry, clean, load-bearing, absorbent and free of adhesion impairing residues, efflorescence and sinter skins.■ For assessing the plaster primer, VOB/C DIN 18350, Section 3, DIN EN 13914-1/13914-2 as well as the plaster standard DIN 18550-1/18550-2 should be observed.
Pretreatment	<ul style="list-style-type: none">■ Completely remove non-load-bearing plaster, coatings or salt efflorescence.■ Highly absorbent substrates are to be pre-treated.■ Allow rough cast to harden for at least 1 day depending on temperature and weathering.

PROCESSING

Temperature	<ul style="list-style-type: none"> Do not process or allow to dry out at air, material or substrate temperatures below +5°C, or if there is a risk of exposure to night frost, or at temperatures above +30°C, or in direct sunlight, or on heated up surfaces, and/or in windy conditions.
Mixing / Preparation / Processing	<ul style="list-style-type: none"> Suitable for processing by hand, or with conventional plastering machines. When machine-processing: Adjust the amount of water accordingly to obtain a workable consistency. If the work is interrupted for longer periods, then clean the plastering machine and mortar hoses. When mixing manually, first place the quantity of water specified in the technical data in a clean container and then sprinkle in dry mortar. Use clean tap water. use a suitable agitator to mix the material until smooth and free of lumps. Leave to rest for a moment and then mix again, adding more water, if required, to achieve the right consistency for applying. Do not mix with other products and/or other substances.
Processing	<ul style="list-style-type: none"> Apply mortar evenly in layer thicknesses from approx. 15 mm to the prepared substrate. Basically, work in two shifts, wet in wet. Plaster layer thicknesses of more than 20 mm in one layer are not recommended. The layer thickness must not be less than 10 mm. When plastering in two layers, the first layer is to be well roughened and pre-wetted before applying the second layer. Before applying the second layer, a rest time must be planned until a carbonation depth of approx. 5 mm in the first layer is reached. The second plaster layer, depending on the type of subsequent coating, is evenly roughed up or felted off.
Processing / Working time	<ul style="list-style-type: none"> Approximately 1 hour The stated times apply for a temperature of +20°C and relative humidity of 65%. Mortar that has already started to harden must never be thinned down with additional water, remixed or applied.
Drying / Hardening	<ul style="list-style-type: none"> If the weather conditions are unfavourable (e.g. driving rain, frost, strong sunlight and/or winds), then suitable protection measures must be taken, particularly in the case of freshly coated surfaces. To avoid too rapid water removal, the plastered surface should be kept moist for approx. 10-14 days, depending on the weather. Before applying a coat of paint, the plaster surface must be sufficiently solid and completely dry.
Subsequent coating / Suitability for coating	<ul style="list-style-type: none"> Before applying a coat of paint, the plaster surface must be sufficiently solid and completely dry. A coat of mineral paint may be applied after approx. 8 weeks at the earliest.
Cleaning the tools	<ul style="list-style-type: none"> Clean all tools and equipment with water immediately after use.
Notes	<ul style="list-style-type: none"> Carefully cover adjacent surfaces and components (e.g. windows, window sills, etc.). Wash off contamination immediately with water.

PACKAGING

- 25 kg/sack

STORAGE

- Store dry and as per instructions.

QUANTITY REQUIRED / YIELD

- consumption: approx. 23 kg/m² per 15 mm plaster thickness
- yield: app. 16 l fresh mortar per 25 kg/sack

TECHNICAL DATA

Product type	standard plastering mortar GP
Category	CS I
Compressive strength	approx. 2,5 N/mm ²
Grain	0 – 1 mm, 0 – 2 mm, 0 – 4 mm, 0 – 8 mm
Water requirement	approx. 7.5 l per 25 kg/sack
Set mortar bulk density	approx. 1.4 kg/dm ³
Fire behaviour	A1 (non-flammable) in accordance with EN 13501
Adhesive tensile strength	≥ 0.08 N/mm ²
Capillary water absorption	W _{c,0} according to EN 998-1
Water vapour permeability μ	app. 5 - 7
Thermal conductivity λ_{10,dry,mat.} for P=50%	≤ 0.82 W/(mK)
Thermal conductivity λ_{10,dry,mat.} for P=90%	≤ 0,89 W/(mK)

All data are average values that were determined under laboratory conditions according to relevant test standards and application tests. Deviations are possible under practical conditions.

SAFETY AND DISPOSAL INSTRUCTIONS

Safety	<ul style="list-style-type: none"> ■ This product produces an alkaline reaction when it comes into contact with moisture/water. Therefore ensure that skin and eyes are protected. If it should come into contact with the skin or eyes, rinse them thoroughly with water. See a doctor immediately if it comes into contact with the eyes. ■ Further information can be found in the safety data sheet at www.tubag.de.
Disposal	<ul style="list-style-type: none"> ■ Completely empty and recycle the packaging. ■ Dispose of the material in accordance with the official regulations. ■ Dispose of hardened product in accordance with the local regulations. Do not allow to enter the sewer system. Dispose of the hardened product in the same way as concrete waste and slurries. Waste code according to the Ordinance on the European Waste Catalogue depending on the origin: 17 01 01 (concrete) or 10 13 14 (concretewaste and concrete slurries).

GENERAL INFORMATION

This information sheet provides only general recommendations. Should you have any queries relating to a specific application, please contact our technical sales advisor or call our hotline: +49 541 601-601. All of the details given are based on our current knowledge and experience and on the assumption that the materials are professionally applied and used for their normal purpose. All of the details are non-binding and do not release users from their duty to undertake their own tests to ensure suitability for the intended application. Due to the effects of different weather, processing and construction site conditions, no guarantee can be given for the general validity of all details. We reserve the right to make changes as a result of further development of the product and applications engineering. The general rules for construction engineering, the valid standards and guidelines, and the technical working guidelines must be observed. The publication of this technical data sheet renders all previous editions of this data sheet void. Please obtain the latest information from our website.

FL-P

Historical lime plaster

