



Solvent-free, bituminous primer

- rainproof: after approx. 3 hours
- fully dry: at least 12 hours



APPLICATIONS

- for dust suppression and improved adhesion on bituminous and mineral substrates
- for preparing the substrate and binding dust especially in the roof area
- to improve adhesion for the following bituminous protective and sealing coats
- for interior use as pre-treatment before bonding bitumen membranes
- for external and interior use

PROPERTIES

- solvent-free
- ready for use
- weak odor
- rollable and spreadable
- Colour: black

COMPOSITION

- Material basis: Bitumen emulsion

SUBSTRATE

- | | |
|-------------------------|---|
| Properties/tests | <ul style="list-style-type: none">■ The substrate must be dry, load-bearing, clean, dust-free and free of adhesion-reducing residues, release agents, efflorescence and sintered coatings.■ Plasters must be hardened. |
|-------------------------|---|

PROCESSING

- | | |
|---------------------------|---|
| Temperature | <ul style="list-style-type: none">■ Can be used at air, material and substrate temperatures of +5 ° C to +35 ° C. |
| Applying | <ul style="list-style-type: none">■ Apply the product over the entire surface, thinly, with a brush, roller or a suitable tool. |
| Drying / Hardening | <ul style="list-style-type: none">■ The fresh bitumen primer is water-soluble and must be protected from water loads until it is dried out.■ Protect from drying out too quickly and unfavorable weather conditions (frost, rain, etc.)■ Depending on the weather and temperature, maintain a drying time of at least 12 hours before any subsequent application. |
| Notes | <ul style="list-style-type: none">■ No water may get between the substrate and the primer during the construction phase. |



PACKAGING

- 10 l/bucket
- 25 l/bucket

STORAGE

- Store in the original, unopened packaging in dry, frost-free conditions.

QUANTITY REQUIRED / YIELD

- consumption: approx. 150 ml/m² per application

TECHNICAL DATA

Crack bridging class

Rain resistance after approx. 3 hours

Drying time at least 12 hours

Temperature resistance, permanent -20°C to +80°C

All data are average values that were determined under laboratory conditions according to relevant test standards and application tests. Deviations are possible under practical conditions.

SAFETY AND DISPOSAL INSTRUCTIONS

- Completely empty and recycle the packaging.
- Dispose of the material in accordance with the official regulations.

GENERAL INFORMATION

This information sheet provides only general recommendations. Should you have any queries relating to a specific application, please contact our technical sales advisor or call our hotline: +49 541 601-601. All of the details given are based on our current knowledge and experience and on the assumption that the materials are professionally applied and used for their normal purpose. All of the details are non-binding and do not release users from their duty to undertake their own tests to ensure suitability for the intended application. Due to the effects of different weather, processing and construction site conditions, no guarantee can be given for the general validity of all details. We reserve the right to make changes as a result of further development of the product and applications engineering. The general rules for construction engineering, the valid standards and guidelines, and the technical working guidelines must be observed. The publication of this technical data sheet renders all previous editions of this data sheet void. Please obtain the latest information from our website.