



BUILD – RENOVATE – REPAIR

BZ Flash cement

fast hardening mounting filler



TECHNICAL INFORMATION

Compressive strength	≥ 20 N/mm ²
Processing consistency	weakly plastic
Processing temperature	+5°C up to +35°C
Processing time	approx. 1 minute

All data are average values that were determined under laboratory conditions according to relevant test standards and application tests. Deviations are possible under practical conditions.

PROPERTIES

- compressive strength: ≥ 20 N/mm²
- processing time: approx. 2 minutes
- load-bearing after a few minutes thanks to rapid cement
- weather and frost resistant after hardening
- easy to mix
- waterproof

APPLICATIONS

- for all assembly work, in particular for doweling, anchoring and fastening
- for urgent repair work on concrete
- for plugging openings in walls
- for external and interior use

QUALITY

- quality-monitored
- low-chromate

PROCESSING

Do not process at air, material and substrate temperatures below +5 °C.

Sprinkle instant cement into a measured amount of water (0.18 l/ kg) in a rubber cup or similar and mix ready for processing.

Substrates must be pre-wetted. Press instant cement into the intended holes and immediately bring anchors into the final position. When inserting the instant cement, care must be taken to ensure void-free processing. Protect instant cement processed outdoors against penetrating moisture, e.g. by means of covers. Please mix only as much instant cement as can be processed in a few minutes. Do not use stiffened instant cement anymore. Instant cement must not be brought into contact with non-ferrous metals such as zinc, lead, copper and aluminium (risk of corrosion).

The mixed product can be processed at +20 °C for about 2 minutes.

Clean all tools and equipment with water immediately after use.

CONSUMPTION

consumption: depending on application

STORAGE

Store dry and as per instructions.

PACKAGING

- 1 kg/cup
- 5 kg/bag
- 10 kg/bag
- 15 kg/bucket

DISPOSAL

Completely empty and recycle the packaging.

NOTE

This product produces an alkaline reaction when it comes into contact with moisture/water. Therefore ensure that skin and eyes are protected. If it should come into contact with the skin or eyes, rinse them thoroughly with water. See a doctor immediately if it comes into contact with the eyes.



BUILD – RENOVATE – REPAIR

BZ Flash cement

fast hardening mounting filler

The statements are made based on extensive tests and practical experiences. They cannot be applied to every application case. Therefore, we recommend carrying out application trials if necessary. Subject to technical changes in the course of further development. Furthermore, our General Terms and Conditions of Business apply.

30.01.2023

EMERGENCY NUMBER: +49 551 19 240

quick-mix is a Sievert brand
Sievert Baustoffe SE & Co. KG
Mühlenschweg 6 • 49090 Osnabrück • Phone +49 541 601-01 • Fax +49 541 601-853 • info@quick-mix.de • www.quick-mix.de