

# akurit Fire-stop panel 035 HP coated both sides

fire-stop panel according to DIN  
EN 13162 made of non-flammable  
mineral wool (MW) – building material class A1

- thermal conductivity:  $\lambda = 0.035 \text{ W/(mK)}$
- dimensions: 1200 x 200 mm



## Applications

- for use in flame retardant ETICS with EPS insulation panels

## Properties

- behaviour in fire A1 - non-flammable
- heat and sound insulating
- sound absorbing
- vapour-permeable
- chemically neutral
- dimensionally and form stable
- age-resistant
- pressure resistant

## Substrate

### Condition / Testing

- The substrate must be dry, clean, load-bearing, dust-free, absorbent and free of adhesion-reducing residues, release agents, efflorescence and sintered coatings.
- The load-bearing capacity, particularly of old plaster and old paintwork, must be properly tested (e.g. by carrying out a pull-out test or cross-cut test).
- The insulating material should only be processed on dry substrates to prevent discolouration on the facade.

### Pretreatment

- Uneven areas can be bridged up to 1 cm/m with bonded and up to 2 cm/m with bonded and anchored ETICS systems. Larger uneven areas in the substrate must be levelled mechanically or by applying a levelling plaster.

## Processing

### Temperature

- Do not process or allow to dry out at air, material or substrate temperatures below +5°C, or if there is a risk of exposure to night frost, or at temperatures above +30°C, or in direct sunlight, or on heated up surfaces, and/or in windy conditions.

### Mixing / Preparing / Processing

- Cut insulation panels to length with an insulation knife or a saw.

### Applying / Processing / Assembling

- The insulation panels are fastened according to the specifications of the respective ETICS-approval/type approval
- Caution: Adhesive side = panel side with uncoated stripes
- Bonding over the whole area in the combed bed method on even substrates: Apply adhesive mortar with a notched trowel over the whole area on the back of the panel.
- Position insulation panels tightly immediately, at the latest however 10 minutes after applying the adhesive, with at least 10 cm overlap butt jointed. Then press on the panels with a large, clean plastering float.
- Do not allow any adhesive mortar to get into the panel joints.
- On building corners, the insulation panels are to be interlinked in panel thickness. Take care to form the corners perpendicular and flush.
- Existing building expansion joints must be adopted in the external thermal insulation composite system with special expansion joint profiles.

# akurit Fire-stop panel 035 HP

## coated both sides

### Drying / Hardening

- The required intermediate rest time depends on the adhesive mortar used and the ambient and structure temperature.
- The drying and hardening process will be slowed down by low temperatures and/or high air humidity and accelerated by high temperatures and/or low air humidity.
- Insulated areas are to be protected from the effect of extreme damp and direct sunshine using suitable measures e.g. by covering the scaffolding. Apply reinforcement layer quickly.

### Subsequent coating / workability

- It is possible to process bonded panels further once the adhesive mortar has hardened sufficiently.
- The necessary anchoring and the application of the reinforcement layer are possible once the adhesive mortar has hardened sufficiently.

### Notes

- Take into consideration the respective system permissions when using the product in thermal insulation composite systems.
- The processing in special situations is described in Technical System Information 6, "ETICS systems on the subject of fire protection", issued by the trade association for external thermal insulation composite systems.
- For more execution information about processing the product in the ETICS, see brochure "ETICS - basic principles and planning".
- The panels must be anchored according to the structural analysis or the details according to the general building approval / general type approval issued by the DIBt that belongs to the system.
- Damaged or soaked insulation panels must not be installed. Adhesive mortar in the panel joints, the use of contaminated leftover panels as well as patchwork must be avoided.

### Storage

- Store dry and as per instructions.
- Protect against direct sunlight.

### Technical Data

<b>Designation key</b>	MW-EN 13162 T5-DS(70,-)-DS(70,90)-CS(10)10-TR5-WS-WL(P)-MU1
<b>Application abbreviation</b>	WAP-zg according to DIN 4108-10
<b>Adhesive coating</b>	coated both sides
<b>Panel format</b>	L x W (mm): 1200 x 200
<b>Fire behaviour</b>	A1 (non-flammable) in accordance with EN 13501
<b>Melting point</b>	≥ 1000 °C according to DIN 4102-17
<b>Nominal value of thermal conductivity <math>\lambda</math></b>	0.034 W(mK) according to DIN EN 13162
<b>Rated value of the thermal conductivity <math>\lambda</math></b>	0,035 W(mK) according to EN 13162
<b>Specific thermal capacity</b>	1030 J/(kgK) according to EN 12524
<b>Water vapour diffusion resistance <math>\mu</math></b>	1 according to EN 12086
<b>Tensile strength vertical to panel plane</b>	≥ 5 kPa according to DIN EN 1607
<b>Compressive strength in case of 10 % compression</b>	≥ 10 kPa according to DIN EN 826
<b>Dimensional stability at defined temperature</b>	DS(70,-) according to EN 1604
<b>Dimensional stability at defined temperature and humidity conditions</b>	DS(70,90) according to EN 1604
<b>Long term water absorption</b>	WL(P) according to EN 12087

### General notes

This information sheet provides only general recommendations. Should you have any queries relating to a specific application, please contact our technical sales advisor or call our hotline: +49 541 601-601. All of the details given are based on our current knowledge and experience and on the assumption that the materials are professionally applied and used for their normal purpose. All of the details are non-binding and do not release users from their duty to undertake their own tests to ensure suitability for the intended application. Due to the effects of different weather, processing and construction site conditions, no guarantee can be given for the general validity of all details. We reserve the right to make changes as a result of further development of the product and applications engineering. The general rules for construction engineering, the valid standards and guidelines, and the technical working guidelines must be observed. The publication of this technical data sheet renders all previous editions of this data sheet void. Please obtain the latest information from our website.