



### Solvent-based, bituminous primer

- frost-resistant
- rainproof: after approx. 3 hours
- fully dry: approx. 12 hours



### APPLICATIONS

- for improving adhesion on mineral substrates
- for improving adhesion on bitumen roof membrane
- for external use

### PROPERTIES

- ready for use
- liquid
- weak odor
- good penetration
- rollable and spreadable

### SUBSTRATE

<b>Suitable substrates</b>	<ul style="list-style-type: none"><li>■ mineral-bound substrates</li><li>■ Bitumen waterproofing membranes</li><li>■ does not fit for application on expand and extrude polystyrene</li></ul>
<b>Properties/tests</b>	<ul style="list-style-type: none"><li>■ The substrate must be frost-free, dry on the surface, sustainable, clean, and free from contamination and separating layers of all kinds (e.g. paint coatings, formwork oils).</li><li>■ Plasters must be hardened.</li></ul>
<b>Pretreatment</b>	<ul style="list-style-type: none"><li>■ Remove loose particles, dust and adhesion-depleting contaminants.</li></ul>

### COMPOSITION

- Material basis: Bitumen
- with added adhesive

### PROCESSING

<b>Temperature</b>	<ul style="list-style-type: none"><li>■ Can be used at air, material and substrate temperatures of +5 °C to +35 °C.</li></ul>
<b>Applying</b>	<ul style="list-style-type: none"><li>■ Apply the product over the entire surface, thinly, with a brush, roller or a suitable tool.</li></ul>
<b>Drying / Hardening</b>	<ul style="list-style-type: none"><li>■ Can be worked over after approx. 12 hours drying time (at +20 °C and 65% relative humidity).</li><li>■ Protect from drying out too quickly and unfavorable weather conditions (frost, rain, etc.)</li></ul>



### PACKAGING

- 10 l/bucket
- 25 l/bucket

### STORAGE

- Store dry and as per instructions.
- Protect against direct sunlight.

### QUANTITY REQUIRED / YIELD

- consumption: approx. 0.15 l/m<sup>2</sup>

### TECHNICAL DATA

<b>Crack bridging class</b>	RÜ3-E according to DIN 18533
<b>Rain resistance</b>	after approx. 3 hours
<b>Drying time</b>	approx. 12 hours
<b>Temperature resistance, permanent</b>	-20°C to +100°C

All data are average values that were determined under laboratory conditions according to relevant test standards and application tests. Deviations are possible under practical conditions.

### SAFETY AND DISPOSAL INSTRUCTIONS

<b>Safety</b>	■ Follow further instructions in the safety data sheet.
<b>Disposal</b>	■ Completely empty and recycle the packaging. ■ Dispose of the material in accordance with the official regulations.

### GENERAL INFORMATION

This information sheet provides only general recommendations. Should you have any queries relating to a specific application, please contact our technical sales advisor or call our hotline: +49 541 601-601. The technical data refer to + 20 ° C and 60% relative humidity. All of the details given are based on our current knowledge and experience and on the assumption that the materials are professionally applied and used for their normal purpose. All of the details are non-binding and do not release users from their duty to undertake their own tests to ensure suitability for the intended application. Due to the effects of different weather, processing and construction site conditions, no guarantee can be given for the general validity of all details. We reserve the right to make changes as a result of further development of the product and applications engineering. The general rules for construction engineering, the valid standards and guidelines, and the technical working guidelines must be observed. The publication of this technical data sheet renders all previous editions of this data sheet void. Please obtain the latest information from our website.